

ROW, INC.

Manufacturer of TFE-O-SIL[®] O-Rings & Gaskets Since 1976
FEP & PFA Encapsulated Silicone, Fluoroelastomer & EPDM

VITON[®] - 60 DUROMETER

Cam & Groove Coupling Gasket Compound

Viton[®] fluoroelastomer terpolymer compound
with improved chemical resistance

<u>Original Properties</u>	<u>ASTM D2000 Test Method</u>	<u>Requirement</u>	<u>Result</u>
Durometer, Shore A	D2240	60 ± 5	60
Tensile strength, MPa (psi)	D 412	10.0 (1450)	11.0 (1600)
Elongation, %	D 412	200	375
100% Modulus, MPa (psi)	D 412	n/a	1.7 (250)
Specific Gravity	D 297	n/a	1.88

Compression Set 22 Hours @ 200°C (392°F)

% of original deflection, max.	D 395	50	8
--------------------------------	-------	----	---

Service Temperature Range °C (°F) -26° to +205°C (-15° to + 400°F)

Color: Black

Fluorine Content: 68%

729 W. Winthrop Avenue • Addison, IL 60101
Phone: 800-770-7128 / 630-628-9221 • Fax: 630-628-9229
Web: www.row-inc.com • Email: sales@row-inc.com