

ROW, INC.

Manufacturer of TFE-O-SIL[®] O-Rings & Gaskets Since 1976
FEP & PFA Encapsulated Silicone, Fluoroelastomer & EPDM

VITON[®] - 75 DUROMETER

USP Class VI compliant – Bisphenol Cured

FDA Conforming – Title 21 CFR 177.2600

3A Sanitary Standard compliant

<u>Original Properties</u>	ASTM D2000 <u>Test Method</u>	<u>Requirement</u>	<u>Result</u>
Durometer, Shore A	D2240	75 ± 5	75
Tensile strength, MPa (psi)	D 412	7.0 (1015)	9.31 (1350)
Elongation, %	D 412	175	275
100% Modulus, MPa (psi)	D 412	n/a	7.0 (1010)
Specific Gravity	D 297	n/a	2.00

Compression Set 22 Hours @ 150°C (302°F)

% of original deflection, max.	D 395	50	28.5
--------------------------------	-------	----	------

Service Temperature Range °C (°F) -29° to +205°C (-20° to + 400°F)

Color: Black

729 W. Winthrop Avenue • Addison, IL 60101
Phone: 800-770-7128 / 630-628-9221 • Fax: 630-628-9229
Web: www.row-inc.com • Email: sales@row-inc.com